



**PAG.** 1/2

SIZES 36 - 47



HEAT RESISTANCE SOLE UP TO 300°C SOLE TOE REINFORCEMENT

CARBONLIGHT TOE CAP

Non-metallic and ultra-light toe cap against pressure up to 200 joules.

Extra protection and resistance.



RESISTANCE TO WATER ABSORPTION

CARBONLIGHT TOE CAP Q-FLEX INSOLE

### NORMS EN ISO 20345:2011

S3 - Closed heel area with the following characteristics:

- A Antistatic footwear
- E Heel energy absorption
- FO Resistance to fuel oil of the outsole
- P Penetration resistance sole
- WRU Water penetration resistant uppers

#### ADDITIONAL CHARACTERISTICS:

**SRC** - Slip resistance on ceramic + sodium lauryl sulfate and steel + glycerin **HRO** - Resistance to hot contact of the outsole

## ADVANTAGES

Breathable | Comfortable | Excellent anti-slip features | Water-resistant materials | Non-metallic

### WORKING ENVIRONMENT

outsole safer and cleaner

100% NON METALLIC

MECHANIC | CONSTRUCTION | ENGINEERING | OIL PLATFORMS | OUTDOOR JOBS

Se MICHELI



The information contained in this document may change without notice. For more information, please visit our website **TOWORKFOR.PT**  NITRILE RUBBER





## **PIT STOP** 6A03.10 S3 SRC HRO



PAG. 2/2 CERTIFICATION NUMBER



# **TECHNICAL INFORMATION**

MATERIALS	STANDARDS	DESCRIPTION	UN.	RESULTS	REQ. EN ISO 20345:2011
<b>UPPER</b> - BLACK FLOATER - PRINTED LEATHER - Long lasting, flexi breathable, and water resistannt materials.	6.3 6.13	WATER VAPOUR PERMEABILITY COEFFICIENT OF PERMEABILITY TEARING STRENGTH TRANSMITED WATER AFTER 60 MIN ABSORVED WATER 60 MIN	mg/cm² mg/cm² N g %	9,7 83,4 321 0 4.5	min. 0,8 min. 15 min. 120 max. 0,2 max. 30
<b>UPPER LINING</b> POROMAX - Innovative technology due to the structure of the internal chambers that removes hot and moist air from the top of the shoe and facilitates the uniform distribution of temperature inside the shoes.	6.6+6.8 6.3	WATER VAPOUR PERMEABILITY COEFFICIENT OF PERMEABILITY TEARING STRENGTH	mg/cm² mg/cm² N	120,4 963,0 41,9	min. 2,0 min. 20 min. 15
<b>HEEL LINING</b> CAMBRELLE - Offer a combination of abrasion resistance and moisture management to keep feet cool, dry, and comfortable even in extreme conditions.	5.5.1 6.12	TEARING STRENGTH Abrasion Resistance (DRY) Abrasion Resistance (Wet)	N - -	18 approved approved	min. 15 51.200 25.600
<b>INSOLE</b> Q-FLEX - Anti-perforation, non-metallic and anti-static insole.	6.2.1.1	PERFORATION RESISTANCE	Ν	approved	no perforation
<b>INSOCK</b> BIORELAX - Anti-fatigue , antibacterial and 100% breathabl	e. 5.5.2 7.2	ABRASION RESISTANCE (DRY) ABRASION RESISTANCE (WET) WATER DESORPTION WATER ABSORPTION	cycles cycles % mg/cm2	approved approved - -	25.600 12.800 min 80 min 70
<b>SOLE</b> MICHELIN NORTH NITRILE RUBBER - The Michelin North sole it's multifunctional, designed for all outdoor work activities allowing full control.	8.2 8.3 8.4 8.6	TEARING STRENGTH ABRASION RESISTANCE BENDING RESISTANCE OIL RESISTANCE VOLUME VARIATION OIL RESISTANCE INCREASED TOUGHNESS	N/mm mm <sup>3</sup> mm % Shore A	9,8 100 - 2,1 <10	min. 4,0 max. 150 max. 4 max 12 max 10
FULL SHOE	5.11 5.4 5.5 5.14 5.2	SLIP RESISTANCE IN CERAMIC WITH WATER AND DETERGENT SLIP RESISTANCE IN STAINLESS WITH GLYCERINE IMPACT RESISTANCE COMPRESSE STRENGTH SHOCK ABSORPTION (HEEL) ADHESION STRENGTH SOLE/CUT	flat heel flat mm mm J N/mm	0,38 0,34 0,20 0,16 21,0 20,0 101 6,2	min. 0,32 min. 0,28 min. 0,18 min. 0,13 min. 14,0 min. 14,0 min. 20 min. 4,0

#### SHOE WEIGHT (SIZE 42): 674g